

XYRON™ X423V

Asahi Kasei Corporation - Polyphenylene Ether + PS

General Information
Product Description

 Modified PPE
 30% Filler reinforced
 Stiffness High, Warpage Low

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • North America
Filler / Reinforcement	• Glass Fiber/Mineral, 30% Filler by Weight
Features	• Flame Retardant • Halogen Free • Low Warpage
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PPE+PS-(GF+MD)30FR(40)<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183
Molding Shrinkage ² (0.0787 in)	0.19 to 0.33	%	Internal Method
Water Absorption (24 hr, 73°F)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 73°F)	12200	psi	ISO 527
Tensile Strain (Break, 73°F)	2.0	%	ISO 527
Flexural Modulus (73°F)	1.06E+6	psi	ISO 178
Flexural Stress (73°F)	19100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (73°F)	2.4	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	223	°F	ISO 75-2/A
CLTE - Flow (-22 to 149°F)	1.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (-22 to 149°F)	3.3E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (73°F)	1.0E+16	ohms·cm	IEC 60093

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	194 to 212	°F
Drying Time - Hot Air Dryer	2.0 to 4.0	hr
Processing (Melt) Temp	464 to 572	°F
Mold Temperature	122 to 176	°F

Notes
¹ Typical properties: these are not to be construed as specifications.

² 150x150x2 mm

³ 4 mm
