

Electrafil® PPS GF35 SS7 BK

 Techmer Polymer Modifiers - *Polyphenylene Sulfide*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight • Stainless Steel Fiber, 7.0% Filler by Weight
UL File Number	• E157318
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.71		ASTM D792
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical			
Tensile Strength (Break)	18000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.90E+6	psi	ASTM D790
Flexural Strength	22000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.4	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	122		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	495	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	500	°F	ASTM D648
CLTE - Flow	1.1E-5	in/in/°F	ASTM D696
Electrical			
Surface Resistivity	1.0E+7	ohms	ASTM D257
Volume Resistivity	1.0E+7	ohms·cm	ASTM D257
Flammability			
Flame Rating	V-0		UL 94

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	325	°F
Drying Time	4.0	hr
Rear Temperature	550 to 580	°F
Middle Temperature	600 to 650	°F
Front Temperature	590 to 630	°F
Nozzle Temperature	600 to 630	°F
Processing (Melt) Temp	615 to 640	°F
Mold Temperature	265 to 325	°F

