

**LATICONTHER 80 CPG/700**

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyphenylene Sulfide*
**General Information**
**Product Description**

High thermal conductivity product based on Polyphenylene Sulphide (PPS). Special filler / Glass fibres. Intrinsically flame retardant. High stiffness. PFAS-free product.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Filler	• Glass Fiber	
Features	• Flame Retardant	• PFAS Free	• Thermally Conductive

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density (73°F)	2.54	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	0.50 to 0.85	%	
Flow : 0.0787 in	0.25 to 0.40	%	
Water Absorption <sup>3</sup> (Saturation, 73°F)	0.010	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	2.10E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	12300	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	0.70	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	1.2	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	3.8	ft·lb/in <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	536	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	527	°F	ISO 75-2/A
Vicat Softening Temperature	509	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	8.3E-6	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	1.7E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
-- <sup>4</sup>	5.6	Btu·in/hr/ft <sup>2</sup> /°F	
-- <sup>5</sup>	6.2	Btu·in/hr/ft <sup>2</sup> /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	580	V/mil	ASTM D149
Comparative Tracking Index <sup>6</sup> (Solution A)	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.030 in	V-0		
0.06 in	V-0		
0.12 in	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
0.04 in	1760	°F	
0.08 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.04 in	1430	°F	



0.08 in

1430 °F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60 MPa

<sup>3</sup> in air

<sup>4</sup> through plane

<sup>5</sup> in plane

<sup>6</sup> without surfactant

