

LATILUB 80-05T G/30

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polyphenylene Sulfide*
General Information
Product Description

Self-lubricating product based on Polyphenylene Sulphide (PPS). PTFE. Glass fibres. Intrinsically flame retardant.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber
Additive	• PTFE Lubricant
Features	• Flame Retardant • Lubricated • High Heat Resistance • Self Lubricating
Uses	• High Temperature Applications

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.61	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	0.50 to 0.75	%	
Flow : 0.0787 in	0.15 to 0.35	%	
Water Absorption ³ (Saturation, 73°F)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.89E+6	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	21000	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	1.5	%	ISO 527-2/5
Coefficient of Friction ⁴			Internal Method
Dynamic	0.35		
Static	0.29		
Wear Factor ⁵	420	10 ⁻¹⁰ in ³ ·min/ft ² ·lb·hr	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.8	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	19	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	527	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	518	°F	ISO 75-2/A
Vicat Softening Temperature	491	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	1.1E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	2.2E-5	in/in/°F	ISO 11359-2
Thermal Conductivity			ASTM E1461
-- ⁶	2.1	Btu·in/hr/ft ² /°F	
-- ⁷	2.1	Btu·in/hr/ft ² /°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	460	V/mil	ASTM D149
Comparative Tracking Index ⁸ (Solution A)	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
0.030 in			



0.06 in	V-0	
0.12 in	V-0	
Glow Wire Flammability Index		IEC 60695-2-12
0.04 in	1760 °F	
0.08 in	1760 °F	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.04 in	1430 °F	
0.08 in	1430 °F	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60 MPa

³ in air

⁴ ISO 7148-2 (speed 0.126 m/s, load 10N)

⁵ ISO 7148-2 (speed 0.126 m/s, load 10N, path length 13.6km)

⁶ through plane

⁷ in plane

⁸ without surfactant

