

InStruc® PPSLGF10

Americhem - Polyphenylene Sulfide

General Information

Product Description

10% GLASS FIBER REINFORCED LINEAR POLYPHENYLENE SULFIDE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Features	• Filled • Good Dimensional Stability	• High Stiffness • High Strength	• Linear Polymer Structure
Uses	• Aerospace Applications • Connectors • Consumer Applications • Electrical/Electronic Applications • Engineering Parts	• Housings • Industrial Applications • Industrial Parts • Metal Replacement • Military/Defense Applications	• Oil/Gas Applications • Outdoor Applications • Semiconductor Applications
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.42		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3 to 5.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	12500	psi	ASTM D638
Tensile Elongation (Yield)	1.0 to 3.0	%	ASTM D638
Flexural Modulus	900000	psi	ASTM D790
Flexural Strength	19500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.90	ft·lb/in	ASTM D256
Unnotched Izod Impact	2.0 to 4.0	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	500	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	300	°F
Drying Time	4.0	hr
Processing (Melt) Temp	610 to 630	°F
Mold Temperature	275 to 350	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

