

LUVOCOM® 1301-50825/BK/EC

 LEHOSS Group - *Linear Polyphenylene Sulfide*
General Information
Product Description

with glass fibers and carbon fibers, electrically conducting; black

Main Features

- Inherent flame resistance.
- Strong, stiff parts.
- Electrically conductive, suitable for continuous discharging of statically-generated electricity.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Filler / Reinforcement	• Carbon Fiber	• Glass Fiber	
Features	• Electrically Conductive	• High Stiffness	• Ignition Resistant
	• Flame Retardant	• High Strength	
Appearance	• Black		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.55	g/cm ³	ISO 1183
Molding Shrinkage			DIN 16742
Across Flow	0.20	%	
Flow	0.70	%	
Water Absorption (24 hr, 73°F)	< 0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.18E+6	psi	ISO 527-1/1
Tensile Stress	27600	psi	ISO 527-2
Tensile Strain (Yield)	1.7	%	ISO 527-2/50
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature ²	428	°F	IEC 60216
Service Temperature - during lifetime max. 200 hr	464	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3 to 1.0E+6	ohms	IEC 62631-3-2
Insulation Resistance ³	1.0E+3 to 1.0E+6	ohms	IEC 62631-3-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		Internal Method

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
--	122 to 194	°F
Desiccant Dryer, A	212 to 284	°F
Drying Time		
--	> 4.0	hr
Desiccant Dryer, A	2.0 to 4.0	hr
Rear Temperature	572 to 608	°F
Middle Temperature	590 to 626	°F
Front Temperature	608 to 644	°F
Nozzle Temperature	608 to 644	°F
Processing (Melt) Temp	626	°F



Injection Notes

During processing, the moisture level should not exceed 0.01%, otherwise molecular degradation may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 20,000 hr

³ strip electrode R25

