

Plaslube® J-1305/30/TF/15 BK5011

Techmer Polymer Modifiers - *Polyphenylene Sulfide*

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.68		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.60E+6	psi	ASTM D790
Flexural Strength	28000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.5	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-0		
0.13 in	V-0		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	325	°F
Drying Time	4.0	hr
Rear Temperature	550 to 580	°F
Middle Temperature	600 to 650	°F
Front Temperature	590 to 630	°F
Nozzle Temperature	600 to 630	°F
Processing (Melt) Temp	615 to 640	°F
Mold Temperature	265 to 325	°F

