

HiFill® PPSU MB7 HF OPAQUE BL515366

 Techmer Polymer Modifiers - *Polyphenylsulfone*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Barium Sulfate
Appearance	<ul style="list-style-type: none"> Blue
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.37		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	380000	psi	ASTM D638
Tensile Strength (Yield)	11000	psi	ASTM D638
Tensile Strength (Break)	10500	psi	ASTM D638
Tensile Elongation (Break)	20	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	2.8	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	275	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	650 to 700	°F
Middle Temperature	660 to 710	°F
Front Temperature	670 to 720	°F
Nozzle Temperature	680 to 730	°F
Processing (Melt) Temp	660 to 725	°F
Mold Temperature	250 to 300	°F
Injection Rate	Slow-Moderate	
Back Pressure	50.0 to 100	psi
Screw Speed	Moderate	

