

HiFill® PPSU 5500 BSF06 LE BL033

Techmer Polymer Modifiers - *Polyphenylsulfone*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Low Extractables
Appearance	• Blue
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Melt Mass-Flow Rate (MFR) (365°C/5.0 kg)	11	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	10200	psi	ASTM D638
Tensile Strength (Break)	8500	psi	ASTM D638
Tensile Elongation (Break)	53	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	3.2	ft-lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	300	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	640 to 730	°F
Middle Temperature	640 to 730	°F
Front Temperature	640 to 730	°F
Nozzle Temperature	640 to 730	°F
Processing (Melt) Temp	680 to 735	°F
Mold Temperature	280 to 325	°F
Injection Rate	Slow	
Back Pressure	0.00 to 100	psi
Screw Speed	Slow-Moderate	

