

InStruc® PSUGF30HF

Americhem - Polysulfone

General Information

Product Description

30% GLASS FIBER REINFORCED, HIGH FLOW POLYSULFONE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Filled • Good Dimensional Stability	• High Flow • High Stiffness	• High Strength
Uses	• Aerospace Applications • Connectors • Consumer Applications • Electrical/Electronic Applications • Engineering Parts	• Housings • Industrial Applications • Industrial Parts • Metal Replacement • Military/Defense Applications	• Oil/Gas Applications • Outdoor Applications • Semiconductor Applications
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.47		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 3.0E-3	in/in	ASTM D955
Water Absorption (Equilibrium)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	20300	psi	ASTM D638
Tensile Elongation (Yield)	1.0 to 3.0	%	ASTM D638
Flexural Modulus	1.10E+6	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.1	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	365	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms-cm	ASTM D257

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	275	°F
Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	660	°F
Mold Temperature	300	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

