

HiFill® PSU LE WT

Techmer Polymer Modifiers - *Polysulfone*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Appearance	• Colors Available
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.24		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	10800	psi	ASTM D638
Tensile Elongation (Yield)	5.0	%	ASTM D638
Flexural Modulus	375000	psi	ASTM D790
Flexural Strength	15900	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.0	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	359	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	345	°F	ASTM D648
CLTE - Flow	4.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257

