

**HiFill® PSU/ABS 1000**

 Techmer Polymer Modifiers - *Polysulfone*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Colors Available</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.13		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Yield)	7000	psi	ASTM D638
Tensile Elongation (Break)	3.8	%	ASTM D638
Flexural Modulus	315000	psi	ASTM D790
Flexural Strength	11900	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	6.0	ft·lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	120		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	300	°F	ASTM D648
CLTE - Flow	3.5E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	550	V/mil	ASTM D149

