

**AuroraFlex™ RE 12283C2UV Clear**

 Aurora Material Solutions, LLC - *Polyvinyl Chloride*
**General Information**
**Product Description**

General purpose

Made in Canada

**General**

Material Status • Commercial: Active

 Availability • Africa & Middle East • Europe • North America  
 • Asia Pacific • Latin America

Features • General Purpose

Uses • General Purpose

Processing Method • Extrusion

**Properties <sup>1</sup>**
**Physical**

	Nominal Value	Unit
Density / Specific Gravity	1.23	

	Nominal Value	Unit
Tensile Strength	2400	psi
Tensile Elongation (Break)	340	%

	Nominal Value	Unit
Durometer Hardness (Shore A, 15 sec)	81	

	Nominal Value	Unit
Brittleness Temperature	-20.2	°F

**Mechanical**

Durometer Hardness (Shore A, 15 sec)

**Hardness**

Brittleness Temperature

	Nominal Value	Unit
Brittleness Temperature	-20.2	°F

	Nominal Value	Unit
Brittleness Temperature	-20.2	°F

