

AuroraFlex™ RE 12055 ULTF NOIR

Aurora Material Solutions, LLC - *Polyvinyl Chloride*
General Information
Product Description

co-extrusion

Made in Canada

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Uses	<ul style="list-style-type: none"> Aerospace Applications Agricultural Applications Appliances Automotive Applications Capstock 	<ul style="list-style-type: none"> Consumer Applications Electrical/Electronic Applications Energy Storage Film Footwear 	<ul style="list-style-type: none"> Furniture Medical/Healthcare Applications Personal Care Sheet
Processing Method	<ul style="list-style-type: none"> Coextrusion 		

Properties ¹

Physical	Nominal Value	Unit
Density / Specific Gravity	1.15	
Mechanical	Nominal Value	Unit
Tensile Strength	1150	psi
Tensile Elongation (Break)	380	%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A, 15 sec)	57	
Thermal	Nominal Value	Unit
Brittleness Temperature	-76.0	°F

