

AuroraFlex™ RE 13355 CF BLANC

 Aurora Material Solutions, LLC - *Polyvinyl Chloride*
General Information
Product Description

General

Made in Canada

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Features	• General Purpose
Uses	• General Purpose
Processing Method	• Extrusion

Properties ¹

Physical	Nominal Value	Unit
Density / Specific Gravity	1.33	
Mechanical	Nominal Value	Unit
Tensile Strength	1330	psi
Tensile Elongation (Break)	400	%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A, 15 sec)	55	
Thermal	Nominal Value	Unit
Brittleness Temperature	-52.6	°F

