

AuroraFlex™ RM 12585

 Aurora Material Solutions, LLC - *Polyvinyl Chloride*
General Information
Product Description

General purpose without DEHP

Made in Canada

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• General Purpose • Non-DEHP Plasticizer
Uses	• General Purpose
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit
Physical		
Density / Specific Gravity	1.25	
Mechanical		
Tensile Strength	2300	psi
Tensile Elongation (Break)	240	%
Hardness		
Durometer Hardness (Shore A, 15 sec)	85	
Thermal		
Brittleness Temperature	5.00	°F

