

AuroraFlex™ RX 12290 LTUV

Aurora Material Solutions, LLC - *Polyvinyl Chloride*
General Information
Product Description

General, low Temperature, phthalate-free

Made in Canada

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• General Purpose • Non-Phthalate Plasticizer • Low Temperature Toughness • UV Absorbing
Uses	• General Purpose
Processing Method	• Extrusion

Properties¹

	Nominal Value	Unit
Physical		
Density / Specific Gravity	1.25	
Mechanical		
Tensile Strength	2790	psi
Tensile Elongation (Break)	260	%
Hardness		
Durometer Hardness (Shore A, 15 sec)	90	
Thermal		
Brittleness Temperature	-22.0	°F

Notes
¹ Typical properties: these are not to be construed as specifications.
