

AuroraFlex™ RX 12370 Natural

 Aurora Material Solutions, LLC - *Polyvinyl Chloride*
General Information
Product Description

General-Phthalate free

Made in Canada

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• General Purpose • Non-Phthalate Plasticizer
Uses	• General Purpose
Processing Method	• Extrusion

Properties ¹

	Nominal Value	Unit
Physical		
Density / Specific Gravity	1.23	
Mechanical		
Tensile Strength	2150	psi
Tensile Elongation (Break)	390	%
Hardness		
Durometer Hardness (Shore A, 15 sec)	70	
Thermal		
Brittleness Temperature	-29.2	°F

Notes
¹ Typical properties: these are not to be construed as specifications.
