

## AuroraTec™ AP4003G

Aurora Material Solutions, LLC - Polyvinyl Chloride

### General Information

#### Product Description

A high rate, Rigid PVC pellet, extrusion compound for interior and exterior applications requiring exceptional impact.

Note: Additional custom color matching is available upon request.

#### General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Features	• Good Rigidity • High Flow • High Impact Resistance
Uses	• Outdoor Applications
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Extrusion

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.45		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	472000	psi	ASTM D638
Tensile Strength	6250	psi	ASTM D638
Flexural Modulus	423000	psi	ASTM D790
Flexural Strength	10800	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	22	ft·lb/in	ASTM D256
Dart Impact <sup>2</sup>			ASTM D4226
Procedure A	1	in·lb/mil	
Procedure B	> 4	in·lb/mil	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Annealed)	162	°F	ASTM D648
CLTE - Flow	3.6E-5	in/in/°F	ASTM D696

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Min Failure

