

**AuroraTec™ AP5142AWH0138**

Aurora Material Solutions, LLC - Polyvinyl Chloride

**General Information**
**Product Description**

A rigid PVC pellet, extrusion compound designed for applications requiring excellent weathering performance, broad processing window, and excellent physical properties. Typical test results for ASTM D-4216. This is a rigid PVC formulation per the requirements of AAMA 303-08. This material meets/exceeds cell class 1-20131-13, as required in ASTM D-4726.

Note: Additional custom color matching is available upon request.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Excellent Weather Resistance	• Good Processability	• Good Rigidity
Uses	• Agricultural Applications • Appliances • Automotive Applications • Consumer Applications • Electrical/Electronic Applications	• Fencing & Decking • Film • Medical/Healthcare Applications • Outdoor Applications • Rail Applications	• Sheet • Spas • Windows & Doors
Agency Ratings	• AAMA 303 08	• ASTM D4726	
Appearance	• Colors Available		
Forms	• Pellets		
Processing Method	• Extrusion		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity <sup>2</sup>	1.47		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	374000	psi	ASTM D638
Tensile Strength	6300	psi	ASTM D638
Flexural Modulus	380000	psi	ASTM D790
Flexural Strength	11400	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	16	ft·lb/in	ASTM D256
Dart Impact <sup>3</sup>			ASTM D4226
Procedure A	1	in·lb/mil	
Procedure B	> 4	in·lb/mil	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	78		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Annealed)	160	°F	ASTM D648
CLTE - Flow	3.2E-5	in/in/°F	ASTM D696

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> white

<sup>3</sup> Min Failure

