

AuroraTec™ AP5166ANT1000

Aurora Material Solutions, LLC - Polyvinyl Chloride

General Information
Product Description

A higher temperature PVC pellet extrusion compound for interior applications.

Note: Additional custom color matching is available upon request.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Uses	• Agricultural Applications	• Fencing & Decking	• Sheet
	• Appliances	• Film	• Spas
	• Automotive Applications	• Medical/Healthcare Applications	• Windows & Doors
	• Consumer Applications	• Outdoor Applications	
	• Electrical/Electronic Applications	• Rail Applications	
Agency Ratings	• NSF STD-51		
Appearance	• Colors Available		
Forms	• Pellets		
Processing Method	• Extrusion		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	500000	psi	ASTM D638
Tensile Strength	6380	psi	ASTM D638
Flexural Modulus	431000	psi	ASTM D790
Flexural Strength	11200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	2.9	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	77		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Annealed)	171	°F	ASTM D648
Ball Pressure Test (185°F)	Pass		IEC 60695-10-2
CLTE - Flow	3.5E-5	in/in/°F	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.04 in		HB	
0.12 in		HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.04 in		1760 °F	
0.12 in		1760 °F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.04 in		1810 °F	
0.12 in		1810 °F	

