

AuroraTec™ AP5141

Aurora Material Solutions, LLC - Polyvinyl Chloride

General Information

Product Description

A high rate, Rigid PVC pellet, extrusion compound for interior applications.
Typical test results for ASTM D-4246.

Note: Additional custom color matching is available upon request.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Rigidity • High Flow		
Uses	• Agricultural Applications • Appliances • Automotive Applications • Consumer Applications • Electrical/Electronic Applications	• Fencing & Decking • Film • Medical/Healthcare Applications • Outdoor Applications • Rail Applications	• Sheet • Spas • Windows & Doors
Agency Ratings	• ASTM D4726		
Appearance	• Colors Available		
Forms	• Pellets		
Processing Method	• Extrusion		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.39		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	400000	psi	ASTM D638
Tensile Strength	6000	psi	ASTM D638
Flexural Modulus	400000	psi	ASTM D790
Flexural Strength	11200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	18	ft-lb/in	ASTM D256
Dart Impact ³			ASTM D4226
Procedure A	1	in-lb/mil	
Procedure B	> 4	in-lb/mil	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	74		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Annealed)	163	°F	ASTM D648
CLTE - Flow	3.7E-5	in/in/°F	ASTM D696

Notes

¹ Typical properties: these are not to be construed as specifications.

² natural

³ Min Failure

