

AuroraTec™ RR 5056 UV2 CLEAR

Aurora Material Solutions, LLC - Rigid Polyvinyl Chloride

General Information

Product Description

Rigid PVC impact modified PVC, transparent

Applications: General extrusion with high UV resistance

Made in Canada

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Impact Modifier		
Features	• Good Rigidity	• Impact Modified	• UV Resistant
Uses	• Agricultural Applications	• Fencing & Decking	• Sheet
	• Appliances	• Film	• Spas
	• Automotive Applications	• Medical/Healthcare Applications	• Windows & Doors
	• Consumer Applications	• Outdoor Applications	
	• Electrical/Electronic Applications	• Rail Applications	
Appearance	• Clear/Transparent		
Processing Method	• Profile Extrusion		

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.32		ASTM D792
Mechanical			
Tensile Modulus	378000	psi	ASTM D638
Tensile Strength	6820	psi	ASTM D638
Flexural Strength	11000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.126 in)	18	ft·lb/in	ASTM D256
Hardness			
Durometer Hardness (Shore D, 15 sec)	78		ASTM D2240
Thermal			
Deflection Temperature Under Load (264 psi, Annealed)	149	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

