

Manner Flexible PVC 6906

Manner Polymers - Flexible Polyvinyl Chloride

General Information

Product Description

Recommended Applications: 80°C (nominal) wire extrusion compound designed for use in JIS type AVS wire and other automotive wire types.

General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Uses	<ul style="list-style-type: none"> Automotive Applications
Processing Method	<ul style="list-style-type: none"> Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31 to 1.35		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	3000	psi	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	41 to 47		ASTM D2240
Additional Information	Nominal Value	Unit	Test Method
Stock Temperature - Recommended Extrusion	375	°F	

Notes

¹ Typical properties: these are not to be construed as specifications.

