

## Manner Flexible PVC M1373

Manner Polymers - Flexible Polyvinyl Chloride

### General Information

#### Product Description

The needs and requirements of the injection molding industry are unique. When choosing a material for an application, several considerations come into play from the end-use application, to how a material flows, to secondary operations.

Manner Plastics can recommend a flexible PVC material to meet the demands of your application. We serve several industries with injection molding applications including footwear, electrical/electronics, and various consumer products.

The table below shows some of our most popular compounds, but is not a comprehensive view of the Manner Plastics product portfolio. If you do not see a compound offering the performance your application requires, please contact us. We may already have a custom formulation that meets your needs.

All the compounds listed below are UL recognized under UL 94, QMFZ2, and QMFZ8.

All Manner Plastic compounds are RoHS compliant.

#### General

|                   |                         |                                      |            |
|-------------------|-------------------------|--------------------------------------|------------|
| Material Status   | • Commercial: Active    |                                      |            |
| Availability      | • North America         |                                      |            |
| Uses              | • Consumer Applications | • Electrical/Electronic Applications | • Footwear |
| Agency Ratings    | • UL 94                 | • UL QMFZ2                           | • UL QMFZ8 |
| RoHS Compliance   | • RoHS Compliant        |                                      |            |
| Forms             | • Pellets               |                                      |            |
| Processing Method | • Injection Molding     |                                      |            |

### Properties <sup>1</sup>

| Physical                                | Nominal Value | Unit | Test Method |
|-----------------------------------------|---------------|------|-------------|
| Density / Specific Gravity              | 1.38 to 1.42  |      | ASTM D792   |
| Elastomers                              | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain, 0.0600 in) | 1570          | psi  | ASTM D638   |
| Tensile Strength (Yield, 0.0600 in)     | 1810          | psi  | ASTM D638   |
| Tensile Elongation (Break, 0.0600 in)   | 180           | %    | ASTM D638   |
| Hardness                                | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore C)            | 70 to 76      |      | ASTM D2240  |
| Thermal                                 | Nominal Value | Unit | Test Method |
| Brittleness Temperature                 | 6.80          | °F   | ASTM D746   |

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

