

Manner Flexible PVC V930

Manner Polymers - Flexible Polyvinyl Chloride

General Information

Product Description

Recommended Applications: 75°C Communication Jacketing compound suitable for drop wire types meeting CM requirements. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Cable Jacketing • Communication Cable Jacketing • Communication Wire Jacketing

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.37 to 1.42		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	2180	psi	ASTM D638
Tensile Elongation ² (Break)	300	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	77 to 83		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-25.6	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ³ (212°F, 240 hr)	-2.0	%	UL Unspecified
Change in Ultimate Elongation in Air ³ (212°F, 240 hr)	-5.0	%	UL Unspecified
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	30	%	ASTM D2863

Notes

¹ Typical properties: these are not to be construed as specifications.

² Unaged Dumbbell: .075 inch

³ Air Aged: .03 inch

