

Manner Flexible PVC X3484

Manner Polymers - Flexible Polyvinyl Chloride

General Information

Product Description

Lead-free general purpose profile and tubing extrusion compound. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General

Material Status	• Commercial: Active
Availability	• North America
Features	• General Purpose • Low (to None) Lead Content
Uses	• Hose • Profiles
RoHS Compliance	• RoHS Compliant
Processing Method	• Extrusion • Profile Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.36 to 1.40		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
0.0600 in	2820	psi	
100% Strain, 0.0600 in	1970	psi	
Tensile Elongation (Break, 0.0600 in)	280	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C)	75		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-9.40	°F	ASTM D746

Notes

¹ Typical properties: these are not to be construed as specifications.

