

Manner Flexible PVC X3570

Manner Polymers - Flexible Polyvinyl Chloride

General Information

Product Description

Lead-free tubing and profile extrusion compound with improved low temperature properties. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General

Material Status	• Commercial: Active	
Availability	• North America	
Features	• Low (to None) Lead Content	• Low Temperature Resistant
Uses	• Profiles	• Tubing
RoHS Compliance	• RoHS Compliant	
Processing Method	• Extrusion	• Profile Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.26 to 1.30		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
0.0300 in	2350	psi	
100% Strain, 0.0300 in	729	psi	
Tensile Elongation (Break, 0.0300 in)	390	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	77		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-65.2	°F	ASTM D746

Notes

¹ Typical properties: these are not to be construed as specifications.

