

Manner Flexible PVC X3602

Manner Polymers - Flexible Polyvinyl Chloride

General Information

Product Description

Lead-free profile extrusion compound suitable for dual extrusion over rigid PVC. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General

Material Status	• Commercial: Active
Availability	• North America
Features	• Low (to None) Lead Content
Uses	• Profiles
RoHS Compliance	• RoHS Compliant
Processing Method	• Coextrusion • Profile Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.24 to 1.28		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
0.0300 in	2140	psi	
100% Strain, 0.0300 in	925	psi	
Tensile Elongation (Break, 0.0300 in)	380	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	75		
Shore A, 15 sec	68		

Notes

¹ Typical properties: these are not to be construed as specifications.

