

AuroraFlex™ 8068NFRV0

Aurora Material Solutions, LLC - *Styrene Ethylene Butylene Styrene Block Copolymer*
General Information
Product Description

A high performance, flame retardant, SEBS based compound designed for Wire & Cable applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Copolymer	• Flame Retardant	
Uses	• Wire & Cable Applications		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.27		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	348	psi	ASTM D412
Tensile Strength	2360	psi	ASTM D412
Tensile Elongation (Break)	830	%	ASTM D412
Tear Strength	213	lbf/in	ASTM D624
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	73		ASTM D2240
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	351 to 379	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	370 to 399	°F
Mold Temperature	70 to 100	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 99.9	psi
Screw Compression Ratio	2.5:1.0 to 3.0:1.0	

Notes
¹ Typical properties: these are not to be construed as specifications.
