

**TRIEL® 5063SPU**
*Samyang Corporation - Thermoplastic Polyester Elastomer*
**General Information**
**Product Description**

TRIEL® offers significant chemical resistance, thermal resistance, weatherability and low temperature flexibility.

**General**

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Uses	• General Purpose	• Industrial Applications	• Industrial Cable Insulation

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.10		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Water Absorption (24 hr, 73°F)	0.50	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength (Yield)	1140	psi	ASTM D638
Tensile Elongation (Yield)	> 400	%	ASTM D638
Flexural Modulus	1420	psi	ASTM D790
Flexural Strength (Yield)	284	psi	ASTM D790
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (73°F)	No Break		ASTM D256
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Durometer Hardness	70 to 75		ASTM D2240

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
