

TRIEL® 5632EM

Samyang Corporation - *Thermoplastic Polyester Elastomer*

General Information

Product Description

TRIEL® offers significant chemical resistance, thermal resistance, weatherability and low temperature flexibility.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Uses	• Electrical/Electronic Applications	• Industrial Applications	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.23		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.118 in)	0.013 to 0.017	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.45	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	4840	psi	ASTM D638
Tensile Elongation (Yield)	> 400	%	ASTM D638
Flexural Modulus	49800	psi	ASTM D790
Flexural Strength (Yield)	2280	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	63		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	243	°F	ASTM D648
Vicat Softening Temperature	392	°F	ASTM D1525

Notes

¹ Typical properties: these are not to be construed as specifications.

