

ADMER™ SE800

Mitsui Chemicals America, Inc. - *Thermoplastic Elastomer*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Adhesives • Coating Applications
Forms	• Pellets
Processing Method	• Cast Film

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.4	g/10 min	ASTM D1238
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	138	°F	ASTM D1525

Notes
¹ Typical properties: these are not to be construed as specifications.
