TRIEL® 5551BM

Samyang Corporation - *Thermoplastic Polyester Elastomer*

General Information

Product Description

TRIEL® offers significant chemical resistance, thermal resistance, weatherability and low temperature flexibility.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Uses	• Automotive Applications	• Automotive Exterior Parts	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.22		ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/10.0 kg	5.0	g/10 min	
230°C/2.16 kg	0.50	g/10 min	
Molding Shrinkage - Flow (0.118 in)	0.015 to 0.017	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.50	%	ASTM D570
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength (Yield)	3840	psi	ASTM D638
Tensile Elongation (Yield)	> 400	%	ASTM D638
Flexural Modulus	17100	psi	ASTM D790
Flexural Strength (Yield)	996	psi	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact	No Break		ASTM D256
Hardness	**Nominal Value**	**Unit**	**Test Method**
Durometer Hardness (Shore D)	55		ASTM D2240
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (66 psi, Unannealed)	187	°F	ASTM D648
Vicat Softening Temperature	345	°F	ASTM D1525

Notes

[1] Typical properties: these are not to be construed as specifications.