

TRIEL® 5559GP

 Samyang Corporation - *Thermoplastic Polyester Elastomer*
General Information
Product Description

TRIEL® offers significant chemical resistance, thermal resistance, weatherability and low temperature flexibility.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Uses	• Food Containers

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.22		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.118 in)	0.017 to 0.020	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.50	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3840	psi	ASTM D638
Tensile Elongation (Yield)	> 400	%	ASTM D638
Flexural Modulus	25700	psi	ASTM D790
Flexural Strength (Yield)	1350	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	50		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	216	°F	ASTM D648
Vicat Softening Temperature	365	°F	ASTM D1525

Notes
¹ Typical properties: these are not to be construed as specifications.
