

AuroraFlex™ 8078BL

Aurora Material Solutions, LLC - *Thermoplastic Elastomer*

General Information

Product Description

8078BL is a black thermoplastic elastomer formulated for applications that require rubberlike properties and a scratch and mar resistant surface finish with a reduced coefficient of friction. 8078BL is well suited for consumer goods and industrial applications requiring UV stability. 8078BL can be overmolded to polypropylene.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• UV Stabilizer		
Features	• Good Scratch Resistance	• Good Surface Finish	• UV Stabilized
Uses	• Consumer Applications	• Industrial Applications	• Overmolding
Appearance	• Black		
Processing Method	• Extrusion	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.02		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	595	psi	ASTM D412
Tensile Strength	1030	psi	ASTM D412
Tensile Elongation (Break)	550	%	ASTM D412
Tear Strength	185	lbf/in	ASTM D624
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	78		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	351 to 379	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	370 to 399	°F
Mold Temperature	70 to 100	°F
Injection Rate	Moderate-Fast	
Back Pressure	50.0 to 99.9	psi
Screw Compression Ratio	2.5:1.0 to 3.0:1.0	

Notes

¹ Typical properties: these are not to be construed as specifications.

