

AuroraFlex™ 3380

Aurora Material Solutions, LLC - *Thermoplastic Elastomer*

General Information

Product Description

AuroraFlex 3380 is a natural S-B-S thermoplastic elastomer formulated for applications that require rubber-like properties and a good surface finish. AuroraFlex 3380 is well suited for consumer goods and various industrial applications. AuroraFlex 3380 can be overmolded and/or coextruded onto polystyrene.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• General Purpose	• Good Surface Finish	
Uses	• General Purpose	• Overmolding	
Appearance	• Natural Color		
Processing Method	• Coextrusion	• Injection Molding	

Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.952		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	943	psi	ASTM D412
Tensile Strength	972	psi	ASTM D412
Tensile Elongation (Break)	72	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	80		ASTM D2240

Processing Information

	Nominal Value	Unit
Injection		
Rear Temperature	351	°F
Middle Temperature	370 to 390	°F
Front Temperature	379 to 399	°F
Nozzle Temperature	390 to 399	°F
Processing (Melt) Temp	390 to 399	°F
Mold Temperature	100 to 120	°F
Injection Rate	Slow-Moderate	
Back Pressure	49.3 to 149	psi
Screw Speed	75 to 125	rpm
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	309 to 320	°F
Cylinder Zone 2 Temp.	320 to 340	°F
Cylinder Zone 3 Temp.	340 to 351	°F
Cylinder Zone 4 Temp.	360 to 370	°F
Cylinder Zone 5 Temp.	351 to 360	°F
Die Temperature	320 to 340	°F

