

AuroraFlex™ GA509ORUV

Aurora Material Solutions, LLC - *Thermoplastic Elastomer*

General Information

Product Description

A 105°C , UV resistant, flame retardant, RoHS Compliant, TPE jacketing material with good low temperature properties.

Note: Additional custom color matching is available upon request.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Flame Retardant	• Low Temperature Toughness	• UV Resistant
Uses	• Jacketing		
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.44 to 1.50		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	2200	psi	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	75 to 81		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deformation - 2 kg (302°F)	37	%	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	42	%	ASTM D2863

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	325	°F
Cylinder Zone 2 Temp.	330	°F
Cylinder Zone 3 Temp.	335	°F
Cylinder Zone 4 Temp.	335	°F
Melt Temperature	340	°F
Die Temperature	345 to 355	°F

