

AuroraFlex™ EXC16013S70A

Aurora Material Solutions, LLC - *Thermoplastic Elastomer*
General Information
Product Description

An SEBS thermoplastic elastomer designed for injection molding applications.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Uses	• General Purpose
Appearance	• Colors Available
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.900		ASTM D792
Melt Mass-Flow Rate (MFR) ² (190°C/5.0 kg)	120	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	69		ASTM D2240

Notes
¹ Typical properties: these are not to be construed as specifications.

² QC range is 105 to 135
