

**AuroraFlex™ GTPE 2011108**

Aurora Material Solutions, LLC - *Thermoplastic Elastomer*
**General Information**
**Product Description**

A 105°C , UV resistant, flame retardant, RoHS Compliant, TPE jacketing material with good low temperature properties.

Note: Additional custom color matching is available upon request.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Flame Retardant	• Low Temperature Toughness	• UV Resistant
Uses	• Jacketing		
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31 to 1.37		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	827	psi	ASTM D638
Tensile Strength	1800	psi	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	72 to 78		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-61.6	°F	ASTM D746
Deformation - 2 kg (302°F)	45	%	UL 2556
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength			
212°F, 96 hr, in Oil	-19	%	
277°F, 168 hr	-5.0	%	
Change in Ultimate Elongation			
212°F, 96 hr, in Oil	-18	%	
277°F, 168 hr	-10	%	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863

**Processing Information**

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	310	°F
Cylinder Zone 2 Temp.	315	°F
Cylinder Zone 3 Temp.	325	°F
Cylinder Zone 4 Temp.	330	°F
Melt Temperature	320	°F
Die Temperature	335 to 340	°F

