

COPEC® CC8OCN (Series: VS/AD1)
KRAIBURG TPE - Thermoplastic Elastomer
General Information
Product Description

The VS/AD1 series is your material solution for consumer electronics applications. It is characterized by a silky and velvety surface. The compounds convince by their adhesion to polar thermoplastics such as ABS, PC or PC/ABS. They are available in black and natural. Naturally colored variants can be coloured in many different ways.

Typical applications

- Seals
- Remote controls
- Ear phones
- Handles and grips for consumer applications
- Handles (hand tools and power tools etc.)
- Games consoles
- Attenuators for electronic housings
- Cell phone covers
- Wearables

Material advantages

- Soft touch surface
- Soft, velvety feel
- Adhesion to PC, ABS, PC/ABS, ASA, SAN
- Insert molding possible
- Resistance to skin oils, sunscreen or olive oil
- Color consistency
- Colorable

Regulations / Approvals

- DIN 75201-B - Fogging
- VDA 270 B3 - Odor
- 49 CFR §571.302 (FMVSS 302)
- DIN EN ISO 105-B06 Methode 3
- VW 50123
- BMW GS 93042
- Mercedes-Benz DBL 5562
- Stellantis B62 0300
- UL 94 HB

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Latin America	• North America
	• Europe	• Oil Resistant	• Soft
Features	• Good Adhesion	• Flexible Grips	• Protective Coverings
	• Good Colorability	• Handles	• Seals
Uses	• Consumer Applications		
	• Electrical Housing		
Agency Ratings	• DIN 75201B		
Automotive Specifications	• BMW GS 93042	• STELLANTIS B62 0300	
	• MERCEDES BENZ DBL 5562	• VOLKSWAGEN 50123	
Appearance	• Natural Color		
Processing Method	• Extrusion	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183

Elastomers

Nominal Value	Unit	Test Method
---------------	------	-------------



Tensile Stress ² (Break)	1380 psi	ISO 37
Tensile Elongation ² (Break)	1000 %	ISO 37
Tear Strength ³	206 lbf/in	ISO 34-1
Compression Set ⁴		ISO 815
73°F, 72 hr	36 %	
158°F, 24 hr	52 %	
Hardness	Nominal Value	Unit
Shore Hardness (Shore A)	78	ISO 48-4
Flammability	Nominal Value	Unit
Flame Rating	HB	UL 94
Additional Information	Nominal Value	Unit
Adhesion to ABS - (D) ⁵	69 lbf/in	VDI 2019
Adhesion to PC - (D) ⁵	63 lbf/in	VDI 2019

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type S2, 7.9 in/min

³ Method Bb, Angle (Nicked)

⁴ Method A

⁵ Two-component injection molding

