

AuroraGuard™ GTPE 220811R

Aurora Material Solutions, LLC - *Thermoplastic Elastomer*
General Information
Product Description

A 105°C PVC jacketing material with good low temperature properties.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Uses	• Jacketing		
Appearance	• Colors Available		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.35		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	1900	psi	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	74		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-49.0	°F	ASTM D746
Deformation - 2kg (302°F)	42	%	UL 2556
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength			
212°F, 96 hr, in Oil	-10	%	
277°F, 168 hr	-15	%	
Change in Ultimate Elongation			
212°F, 96 hr, in Oil	-15	%	
277°F, 168 hr	-16	%	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index ²	32	%	ASTM D2863

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	325	°F
Cylinder Zone 2 Temp.	330	°F
Cylinder Zone 3 Temp.	335	°F
Cylinder Zone 4 Temp.	340	°F
Melt Temperature	340	°F
Die Temperature	340 to 355	°F

