
THERMOLAST® K TC8HFZ (Series: UV/HF/SF)
KRAIBURG TPE - Thermoplastic Elastomer

General Information

Product Description

Applications with long flow paths as well as requirements for UV resistance and surface quality; adhesion to PP

Typical applications

- Water deflectors
- Static window encapsulations
- Roof railing underlays
- Cowls gaskets
- Air guide elements

Material advantages

- Weather resistant, suitable for automotive exterior
- Optimized flow properties
- Surface mapping
- Adhesion to PP
- In-process recycling possible
- Low mold cavity pressure

Regulations / Approvals

- DIN 75201-B - Fogging
- VDA 270 B3 - Odor
- 49 CFR §571.302 (FMVSS 302)
- PV 3930 Florida (1 year)
- PV 3930 Florida (2 years)
- PV 3929 Kalahari (1 year)
- PV 3929 Kalahari (2 years)
- Outdoor Weathering Florida 24 month SAE J1976
- Outdoor Weathering Arizona 24 month SAE J1976
- VW 50123
- BMW GS 93042
- Mercedes-Benz DBL 5562

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Good Adhesion	• Good Weather Resistance	• UV Resistant
	• Good Flow	• Recyclable Material	
Uses	• Automotive Exterior Parts	• Gaskets	
Agency Ratings	• DIN 75201B		
Automotive Specifications	• BMW GS 93042	• MERCEDES BENZ DBL 5562	• VOLKSWAGEN 50123
	• GM GMW16233	• STELLANTIS B62 0300	
Appearance	• Black		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Spiral Flow ^{2, 3}	35.4	in	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ⁴ (Break)	870	psi	ISO 37
Tensile Elongation ⁴ (Break)	520	%	ISO 37



Tear Strength ⁵	108 lbf/in	ISO 34-1	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	77		ISO 48-4

Notes

¹ Typical properties: these are not to be construed as specifications.

² Melt Temperature: 392°F, Injection Pressure: 1.10E+4 psi

³ DSOP Lab 2032

⁴ Type S2, 7.9 in/min

⁵ Method Bb, Angle (Nicked)

