

**THERMOLAST® K TP8VCZ (Series: AD1/CS)**
**KRAIBURG TPE - Thermoplastic Elastomer**
**General Information**
**Product Description**

The AD1/CS series is your material solution for applications with optimized compression set and adhesion to polar thermoplastics such as ABS, PC, PC/ABS, and PBT. The compounds are available in black and natural colors. Natural color variants can be colored in many different ways.

**Typical applications**

- Seals
- Function and design elements
- Cable clips
- Bumpers
- Grommets
- Soft touch surface (thumb wheels, push buttons, switches)

**Material advantages**

- Adhesion to PC, ABS, PC/ABS, ASA, SAN
- Adhesion to PBT
- Optimized compression set
- Optimized mechanical properties

**Regulations / Approvals**

- 49 CFR §571.302 (FMVSS 302)
- VW 50123
- BMW GS 93042
- Mercedes-Benz DBL 5562
- Stellantis B62 0300
- UL 94 HB

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Adhesion • Good Colorability • Good Compression Set • Resilient		
Uses	• Automotive Bumper • Buttons • Grommets	• Knobs • Seals • Soft Touch Applications	• Switches
Automotive Specifications	• BMW GS 93042 • MERCEDES BENZ DBL 5562	• STELLANTIS B62 0300 • VOLKSWAGEN 50123	
Appearance	• Black		
Processing Method	• Extrusion	• Injection Molding	

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm <sup>3</sup>	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (Break)	1450	psi	ISO 37
Tensile Elongation <sup>2</sup> (Break)	600	%	ISO 37
Tear Strength <sup>3</sup>	143	lbf/in	ISO 34-1
Compression Set <sup>4</sup>			ISO 815
73°F, 72 hr	26	%	
158°F, 24 hr	48	%	
212°F, 24 hr	67	%	



<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Shore Hardness (Shore A)	79		ISO 48-4
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating	HB		UL 94
<b>Additional Information</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Adhesion to ABS - (C) <sup>5</sup>	34	lbf/in	VDI 2019
Adhesion to PC - (D) <sup>5</sup>	57	lbf/in	VDI 2019
Adhesion to PC/ABS - (D) <sup>5</sup>	57	lbf/in	VDI 2019

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Type S2, 7.9 in/min

<sup>3</sup> Method Bb, Angle (Nicked)

<sup>4</sup> Method A

<sup>5</sup> Two-component injection molding

