

Milastomer™ G4502BS

Mitsui Chemicals America, Inc. - *Thermoplastic Vulcanizate*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Uses	<ul style="list-style-type: none"> Coating Applications
Appearance	<ul style="list-style-type: none"> Black
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	15	g/10 min	ISO 1133
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (Break)	1970	psi	ISO 37
Tensile Elongation ² (Break)	150	%	ISO 37
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 5 sec)	48		ISO 48

Additional Information

All tests performed according to Mitsui methods.

Notes
¹ Typical properties: these are not to be construed as specifications.

² 20 in/min
