

Milastomer™ 9070BKS

Mitsui Chemicals America, Inc. - *Thermoplastic Vulcanizate*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Flexible Grips • Gaskets
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.890	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	1190	psi	ISO 37
Tensile Stress ² (Break)	1910	psi	ISO 37
Tensile Elongation ² (Break)	640	%	ISO 37
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 5 sec)	38		ISO 48
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°F	Internal Method

Additional Information

All tests performed according to Mitsui methods.

Notes
¹ Typical properties: these are not to be construed as specifications.

² 20 in/min
