

Milastomer™ 7030BS

Mitsui Chemicals America, Inc. - *Thermoplastic Vulcanizate*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Flexible Grips • Gaskets • Weatherstripping
Appearance	• Black
Forms	• Pellets
Processing Method	• Extrusion • Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Density	0.880	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	35	g/10 min	ISO 1133

Elastomers	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Stress ² (100% Strain)	348	psi	ISO 37
Tensile Stress ² (Break)	769	psi	ISO 37
Tensile Elongation ² (Break)	440	%	ISO 37
Compression Set			ISO 815
73°F, 22 hr	29	%	
158°F, 22 hr	43	%	

Hardness	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Shore Hardness			ISO 48
Shore A	72		
Shore A, 5 sec	66		

Thermal	Nominal Value	Unit	Test Method
---------	---------------	------	-------------

Brittleness Temperature	< -76.0	°F	Internal Method
-------------------------	---------	----	-----------------

Additional Information

All tests performed according to Mitsui methods.

Notes
¹ Typical properties: these are not to be construed as specifications.

² 20 in/min
