

Ecomass® 4703ZC87

Ecomass Technologies - Thermoplastic Polyurethane Elastomer

General Information

Product Description

Ecomass® Compound 4703ZC87. Nontoxic alternative to Lead (Pb), weighting and balancing applications.

Features: Moderate Specific Gravity, Stainless Steel Filled Polyurethane (TPU).

General

Material Status	• Commercial: Active
Availability	• Europe • North America
Filler / Reinforcement	• Stainless Steel Powder
Features	• Medium Density • Non-Toxic
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	2.51		ASTM D792
Molding Shrinkage - Flow	6.0E-3 to 9.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	105000	psi	ASTM D638
Tensile Strength	1240	psi	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	84000	psi	ASTM D790
Flexural Strength	8300	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	6.7	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	200	°F
Drying Time	2.0	hr
Processing (Melt) Temp	400 to 430	°F
Mold Temperature	50 to 80	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

