

**LATIOHM 92-03 PD09 F3**

 LATI INDUSTRIA TERMOPLASTICI SPA - *Thermoplastic Polyurethane Elastomer*
**General Information**
**Product Description**

Semiconductive/dissipative product based on Thermoplastic Polyurethane (TPU). Potentially suitable for medical contact application. PFAS-free product.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Antistatic	• Electrically Conductive	• PFAS Free
Uses	• Medical/Healthcare Applications		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.33	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	0.65 to 0.85	%	
Flow : 0.0787 in	0.65 to 0.90	%	
Water Absorption <sup>3</sup> (Saturation, 73°F)	0.22	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	13100	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	No Break		ISO 527-2/5
Tensile Strain (Break, 73°F)	> 50	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	No Break		ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	No Break		ISO 179/1eU
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 1 sec)	95		ISO 7619-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	131	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	122	°F	ISO 75-2/A
Vicat Softening Temperature	122	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	8.3E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	8.3E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	30	ohms	ASTM D257

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60 MPa

<sup>3</sup> in air
