

Fluorolink® E10-H

Perfluoropolyether

Fluorolink® E10-H is a dialcohol terminated, ethoxylated PFPE. Thanks to its functional hydroxyl end-groups, can be used to modify polymers such as urethanes, esters, epoxies and acrylates.

Fluorolink® E10-H is especially suitable as a building block and polymer modifier for those applications that require a combination of excellent water and oil repellency, easy removal of graffiti and fingerprints, low friction, low refractive index and high chemical resistance.

Property	Typical Value	Unit	Test Method
Functional groups	Ethoxylated alcohol		
Average molecular weight (NMR)	1,700	amu	
Fluorine content	57	% w/w	
Kinematic viscosity at 20 °C	115	cSt	
Density at 20 °C	1.69	g/cm ³	
Appearance	Clear, light yellow liquid		

